



Product Name	Color	Spectral Reflectance Pattern	TSR measured range [nm]	Asahikasei Product	Color	Spectral Reflectance Pattern	TSR measured range [nm]
<b>Co Blue 1033</b> Co-Al			43% [300-2100] 56% [800-2100]	<b>Yellow 5970</b> Ti-Cr-Sb			62% [300-2100] 86% [800-2100]
<b>Co Blue 1201</b> Co-Al-Cr			37% [300-2100] 51% [800-2100]	<b>Brown 4128</b> Ti-Fe-Zn			53% [300-2100] 69% [800-2100]
<b>Co Blue 1040</b> Co-Al-Cr			37% [300-2100] 53% [800-2100]	<b>Brown 4080</b> Fe-Zn			38% [300-2100] 52% [800-2100]
<b>Green 2500</b> Co-Cr-Zn-Ti			34% [300-2100] 52% [800-2100]	<b>Brown 4130</b> Fe-Zn-Cr			33% [300-2100] 53% [800-2100]
<b>Green 2024</b> Co-Ni-Zn-Ti			26% [300-2100] 38% [800-2100]	<b>Black 3250LM</b> Cu-Cr-Mn			6% [300-2100] 6% [800-2100]
<b>Yellow 5150</b> Ti-Cr-Sb			71% [300-2100] 88% [800-2100]	<b>Black 3300</b> Cu-Fe-Mn			6% [300-2100] 6% [800-2100]
<b>Yellow 5500</b> Ti-Cr-Sb			68% [300-2100] 87% [800-2100]	<b>Black 6350</b> Fe-Cr			26% [300-2100] 48% [800-2100]

Data or recommendations are based on laboratory preparation and/or testing samples; therefore they can not be expected to fully duplicate commercial production or field performance. Final approval and acceptance should be based on appropriate production and

**Manufacturer**

**ASAHI KASEI KOGYO CO.,LTD.**

1392 Manaita, Gyoda, Saitama 361-0013, Japan

Tel : +81-48-559-1165 Fax : +81-48-559-0921

**Sales agency**

**ASAHI SANGYO KAISHA, LTD.**

1-1-6 Nihonbashi Hongoku-cho, Chuo-ku, Tokyo 103-0021, Japan

Tel : +81-3-5200-8142 Fax : +81-3-5200-8139

E-mail : k.kanno@ns.asahi-san.co.jp