


# Fluorescent Solvent Soluble Toners - 410 Series




## 4 Base Colours




410 Brightener 22



410 Yellow 31




410 Rose 35




410 Magenta 37

## Examples of Colours achievable by blending base colours



**Red 2**

Magenta 37	28.4
Rose 35	3.1
Yellow 31	10.5
Brightener 22	0.0
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>




**Red 3**

Magenta 37	18.0
Rose 35	2.5
Yellow 31	17.5
Brightener 22	4.0
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>




**Orange 4**

Magenta 37	6.5
Rose 35	6.3
Yellow 31	28.5
Brightener 22	0.7
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>




**Orange 5**

Magenta 37	4.0
Rose 35	5.5
Yellow 31	28.5
Brightener 22	4.0
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>




**Orange 6**

Magenta 37	2.0
Rose 35	3.0
Yellow 31	35.5
Brightener 22	1.5
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>



**Green 8**

Magenta 37	0.0
Rose 35	0.0
Yellow 31	32.5
Brightener 22	5.0
Phthalo Green	4.5
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>



**Magenta 10**

Magenta 37	31.5
Rose 35	0
Yellow 31	0
Brightener 22	10.5
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>



**Yellow 27**

Magenta 37	0.0
Rose 35	0.0
Yellow 31	40.5
Brightener 22	0.0
Benzidene Yellow	1.5
Other ingredients	58.0
<b>Total</b>	<b>100.0</b>

NB: Other ingredients will be resin, solvents and waxes as per the customers own formulation

The colours shown here are an indication of the colours achievable at a dry film thickness of 4 microns and are not intended as colour standards  
Users should conduct their own trials to ensure shade and performance meet their requirements



A DANE Group Company  
100 YEARS OF EXCELLENCE